



SymphonyDS™

ARCHITECTURAL WINDOW FILMS



Reflective outside and neutral-looking inside, this series of window films help protect against sun damage, uncomfortable hot spots and annoying screen glare. Minimal dry time also provides immediate clarity.



The Skin Cancer Foundation recommends this product as an effective UV protectant

The Skin Cancer Foundation recommends window film that blocks 99 percent or more of UVA/UVB radiation as effective sun protection. Only SunTek films with 99% or greater UV Protection (300-380nm) have earned the SCF Seal of Recommendation.

SPECIALLY DESIGNED FOR BOTH RESIDENTIAL AND COMMERCIAL APPLICATIONS

SymphonyDS™

ARCHITECTURAL WINDOW FILMS by SunTek®

BENEFITS

- Dual-Reflective, pleasing interior appearance
- Elegant, neutral appearance
- Excellent solar performance
- Advanced UV protection
- Fade and corrosion resistant
- Manufacturer's limited warranty

* Certain restrictions apply; see a dealer for details.



HIGH-TECH INNOVATION

Technology driven systems producing an industry-leading, proprietary process.



A PRICE YOU CAN AFFORD

Innovative and efficient manufacturing delivering lower costs.



EXCEPTIONAL QUALITY

High-quality raw materials converted to meet industry standards.

SymphonyDS™ Series

| PERFORMANCE DATA | SYDS-50 | SYDS-35 | SYDS-25 | SYDS-15 |
|------------------------------|---------|---------|---------|---------|
| Visible Light Transmission | 46% | 40% | 33% | 10% |
| Total Solar Transmission | 41% | 33% | 26% | 7% |
| Total Solar Reflectance | 12% | 21% | 31% | 58% |
| Total Solar Absorbance | 47% | 46% | 43% | 35% |
| Visible Light Reflectance | | | | |
| Interior | 8% | 12% | 18% | 29% |
| Exterior | 12% | 20% | 30% | 63% |
| Winter U-Value | 1.05 | 1.02 | 1.00 | 1.02 |
| Ultraviolet (UV) Protection* | 98% | 98% | 98% | 99% |
| Glare Reduction | 49% | 55% | 64% | 89% |
| Shading Coefficient | 0.64 | 0.54 | 0.44 | 0.20 |
| Solar Heat Gain Coefficient | 0.56 | 0.47 | 0.38 | 0.18 |
| Total Solar Energy Rejection | 44% | 53% | 62% | 82% |

*Wavelengths 300-380nm. Data captured using National Fenestration Rating Council's (NFRC) guidelines on single pane, nominal 1/8 inch (3mm) clear glass. Reported values are taken from representative product samples and are subject to normal manufacturing variances. Actual performance will vary based on a number of factors, including glass type and properties.



345 Beaver Creek Drive TEL 276.632.4991
Martinsville, VA 24112 FAX 276.632.0173 suntekfilms.com

©2022 Eastman Performance Films, LLC. All rights reserved.
No liability is accepted for errors. 04/22. GMN 50185556